

Casque Collection

| GENERAL SPECIFICATIONS | THATCHER, GRIDLOCK, ARCHER, POTHOS, WEBB | COWAN | CROMWELL |
|--|---|---|---|
| Width | 54" | 54" | 54" |
| Weight | 23-24 oz/linear yard | 21 oz/linear yard | 14.6 oz/linear yard |
| Composition | Surface: 94% Polyester, 4% Polyurethane, 2% Silicone Backing: Polyurethane | Surface: 92% Polyester, 6% Polyurethane, 2% Silicone Backing: Polyurethane | Surface: 89% Polyester, 9% Polyurethane, 2% Silicone Backing: Polyurethane |
| Finish | Supreen™ Stain & Moisture Barrier | Supreen™ Stain & Moisture Barrier | Supreen™ Stain & Moisture Barrier |
| Archer Repeat | 9" H x 7.875" V | | |
| Gridlock Repeat | 18" H x .53" V | | |
| Pothos Repeat | 10.5" H x 6.75" V | | |
| Webb Repeat | 6.75" H x 7.32" V | | |
| FLAME RETARDANCY SPECIFICATIONS | | | |
| CAL-TB 117-2013 | Passes | Passes | Passes |
| NFPA 260 | Passes | Passes | Passes |
| UFAC Class 1 | Passes | Passes | Passes |
| PERFORMANCE SPECIFICATIONS | | | |
| Abrasion | 100,000+ DR | 75,000 DR | 100,000+ DR |
| Colorfastness to Crocking | Wet: 4.5 Dry: 4.5 | Wet: 4.5 Dry: 4.5 | Wet: 5 Dry: 5 |
| Seam Slippage | Fill: 80 Warp: 82.5 | Fill: 99.5 Warp: 87.5 | Fill: 83.5 Warp: 94 |
| Tensile Strength | Fill: 80 Warp: 302 | Fill: 145 Warp: 330 | Fill: 79 Warp: 249 |
| Tear Strength | Fill: 93.7 Warp: 69.5 | Fill: 23.4 Warp: 49.7 | Fill: 10.2 Warp: 21.4 |
| Cleaning Code | SW | SW | SW |
| Moisture & Stain Barrier | Yes | Yes | Yes |
| Bleach Resistant | Yes: 10% Dilution | Yes: 10% Dilution | Yes: 10% Dilution |

ENVIRONMENTAL IMPACT

- * This product does not pose any exposure risks associated with the chemical in Prop 65
- * No added flame retardant chemicals
- * No added anti-bacterial / anti-microbial chemicals
- * Lead/ Heavy metal free
- * BPA free / Tris free / Formaldehyde free
- * Does not contain conflict minerals
- * Prop 65 Compliant
- * AB2998 Compliant

RECOMMENDED APPLICATIONS



HOSPITALITY RESTAURANTS WORKPLACE SENIOR LIVING HEALTHCARE



*ACT® Registered Certification Marks

